

Cherishmet Inc.

301 Route 17, Suite 800, Rutherford, NJ 07070 USA
Web site: <http://www.cherishmet.com>



Telephone: (201) 842-7612
Facsimile: (201) 455-6816
Toll Free: (866) 804-0083

AG- 1000W

Model: AG-1000W

Application:

AG-1000W activated carbon is a virgin activated carbon. Produced from anthraciate coal. It is granular in form. Its ideal for many liquid phase applications including the removal of taste and odor compounds and dissolving organics from water stream. The low heavy content and strictly controlled pH level make it particularly attractive for drinking water as well as pharmaceutical level liquid.

Specification:

		ASTM TEST METHODS
Mesh Size:	8x30, 12x40	
Ash(WT%):	10 max.	D2866-94
Moisture:	2% max.	D2867-91
Hardness No.	90 min.	D3802-79
Iodine No.	900 or 950mg/g min.	D4607-94
Density:	0.35-0.55g/ml	D2854-94
Abrasion:	80min.	B604
Water Soluble Ash:	0.2 max.	
Contact pH:	6.5 – 8.0	

Packaging:

Material to be packed in black super sacks with 500kg or 1100lb net each, 2 sacks per pallet. 20-25kg small bags are available.

Remarks:

The above specification can be adjusted in accordance with the customer's requirement.