

Cherishmet Inc.

301 Route 17, Suite 800, Rutherford, NJ 07070 USA
Web site: <http://www.cherishmet.com>



Telephone: (201) 842-7612
Facsimile: (201) 455-6816
Toll Free: (866) 804-0083

AG-1100CW

Model: AG-1100CW

Application:

AG -1100CW is a virgin Acid-Washed activated carbon. Produced from coconut shell. It is granular in form. With the deep hydrochloric acid washed processing, this grade of material meets the requirement of ANSI/NSF 53-1997 which is the standard of Drinking Water Treatment.

Specification:

		ASTM TEST METHODS
Mesh Size:	12x40	
	+12 mesh:	0-5%
	-40 mesh:	0-5%
Ash:	4 % max.	D2866-94
Moisture:	5% max.	D2867-91
Hardness No.	98 min.	D3802-79
Iodine No.	1100mg/g min.	D4607-94
Density:	0.48- 0.53g/cc min. or 30-33lb./cu.ft.	
Abrasion:	70min.	
pH:	6-8	

Packaging:

Material to be packed in black super sacks with 500kg or 1000lb net each, 2 sacks per pallet. 20-25kg small bags are available.

Remarks:

The above specification can be adjusted in accordance with the customer's requirement.