

Cherishmet Inc.

301 Route 17, Suite 800, Rutherford, NJ 07070 USA
Web site: <http://www.cherishmet.com>



Telephone: (201) 842-7612
Facsimile: (201) 455-6816
Toll Free: (866) 804-0083

AG- 900W

Model: AG-900W

Application:

AG-900W activated carbon is a virgin activated carbon. Produced from bituminous coal. It is granular in form. Its ideal for many liquid phase applications including the removal of taste and odor compounds and dissolving organics from water stream. Its superior adsorptive capacity and surface area make it particularly attractive for use with drinking and potable water.

Specification:

		ASTM TEST METHODS
Mesh Size:	8x30, 12x40, 4x10	
Ash(WT%):	15 max.	D2866-94
Moisture:	3% max.	D2867-91
Hardness No.	90 min.	D3802-79
Iodine No.	900mg/g min.	D4607-94
Density:	0.35-0.55g/ml	D2854-94
Abrasion:	80min.	B604

Packaging:

Material to be packed in black super sacks with 500kg or 1100lb net each, 2 sacks per pallet. 20-25kg small bags are available.

Remarks:

The above specification can be adjusted in accordance with the customer's requirement.